


THE STEEL COMPANY OF SCOTLAND, LIMITED.

Test Room Sheet

Newton Works, the *21st* day of *June* 18*94*

ORDER No.	QUALITY.	CHARGE No.	SAMPLE No.	SIZE OF SAMPLE.			BREAKING STRAIN.		EXTENSION.			CONDITION.		INITIAL STRAIN.		SIZE OF FRACTURE.				REMARKS.
				Bth.	Thk.	Area.	Actual Tons.	Per 8" Tons.	% 8 Ins.	% Ins.	% Ins.	Long or Cross.	Annealed or Unannealed.	Actual Tons.	Per 8" Tons.	Bth.	Thk.	Area.	%	
<p><i>Rudder Stock for Messrs Workman & Clarke N^o 110</i></p> <p><i>.90 dia .636 19.1 30.0 13.0 Bent to 91% without fracture 20/6/94</i></p> <p><i>Dropped and hammered with good results 17/5/94</i></p> <p><i>Charles Cooper</i></p>																				



© 2019

Lloyd's Register Foundation

BEL 64-0042

110

Casting.

Reader Stock

Ching Wo

Rel. Rpt. No 4415



© 2019

Lloyd's Register
Foundation