


THE STEEL COMPANY OF SCOTLAND, LIMITED.

*Test Room Sheet*

Newton Works, the 30<sup>th</sup> day of May 1894

ORDER No.	QUALITY.	CHARGE No.	SAMPLE No.	SIZE OF SAMPLE.			BREAKING STRAIN.		EXTENSION.			CONDITION.		INITIAL STRAIN.		SIZE OF FRACTURE.				REMARKS.		
				Bth.	Thk.	Area.	Actual Tons.	Per 6" Tons.	% 8 Ins.	% Ins.	% Ins.	Long or Cross.	Annealed or Unannealed.	Actual Tons.	Per 6" Tons.	Bth.	Thk.	Area.	%			
				<p>Rudder frame for Messrs Workman, Clark &amp; Co's No 110</p> <p>1" dia. 785 22.8 29.0 18.0 Bent to 95% without fracture</p> <p>Dropped &amp; hammered with good results 23/5/94</p> <p>Charles Cooper</p>																		

BEL 64-0046



© 2019

Lloyd's Register  
Foundation



110

Casting.

Rudder frame

Ching Wo

Bel. Rpt. No 4415



© 2019

Lloyd's Register  
Foundation