

THE STEEL COMPANY OF SCOTLAND, LIMITED.

Test Room Sheet *Newton* Works, the *16th* day of *March* 18 *94*

ORDER No.	QUALITY.	CHARGE No.	SAMPLE No.	SIZE OF SAMPLE.			BREAKING STRAIN.		EXTENSION.			CONDITION.		INITIAL STRAIN.		SIZE OF FRACTURE.				REMARKS.
				Bth.	Thk.	Area.	Actual Tons.	Per $\frac{1}{2}$ " Tons.	% 8 Ins.	% Ins.	% Ins.	Long or Cross.	Annealed or Unannealed.	Actual Tons.	Per $\frac{1}{2}$ " Tons.	Bth.	Thk.	Area.	%	
<p><i>Stern Frame for Messrs Workman Clark & Co's N° 110</i></p> <p><i>.89 dia .622 18.1 29.1 21.5 Bent to 90% without fracture</i></p> <p><i>Dropped & hammered with good results 13/3/94 & 24/2/94</i></p> <p><i>Charles Cooper</i></p>																				

© 2019

Lloyd's Register
Foundation

BEL64-0048

110

basting.

Stern Frame

Ching Wo

Bel. Rpt No 4415



© 2019

Lloyd's Register
Foundation