

THE STEEL COMPANY OF SCOTLAND, LIMITED.

Test Room Sheet

Newton Works, the 24th day of March 1894

ORDER NO.	QUALITY.	CHARGE NO.	SAMPLE NO.	SIZE OF SAMPLE.			BREAKING STRAIN.		EXTENSION.			CONDITION.		INITIAL STRAIN.		SIZE OF FRACTURE.				REMARKS.
				Bth.	Thk.	Area.	Actual Tons.	Per ^{sq} Tons.	% 8 Ins.	% Ins.	% Ins.	Long or Cross.	Annealed or Unannealed.	Actual Tons.	Per ^{sq} Tons.	Bth.	Thk.	Area.	%	
<p><i>Stern Frame for Messrs Workman Clark & Co's No 112</i></p> <p><i>.89 dia .622 18.9 30.4 18.5 Bent to 94% without fracture</i></p> <p><i>Dropped and hammered with good results on 9/22/3/94</i></p> <p><i>Charles Cooper</i></p>																				

112

basting.

Stern Frame

"Copack"

Bel. First Entry Rpt. No 4430



© 2019

Lloyd's Register
Foundation