

THE STEEL COMPANY OF SCOTLAND, LIMITED.

Test Room Sheet

Newton

Works, the

27th

day of *June*

1894

ORDER No.	QUALITY.	CHARGE No.	SAMPLE No.	SIZE OF SAMPLE.			BREAKING STRAIN.		EXTENSION.			CONDITION.		INITIAL STRAIN.		SIZE OF FRACTURE.				REMARKS.
				Bth.	Thk.	Area.	Actual Tons.	Per 8" Tons.	% 8 Ins.	% Ins.	% Ins.	Long or Cross.	Annealed or Unannealed.	Actual Tons.	Per 8" Tons.	Bth.	Thk.	Area.	%	
<i>Stern frame for Messrs Workman Clark & Co's No 113</i>																				
<i>Upper part</i>		<i>.96</i>	<i>dia</i>	<i>.723</i>	<i>22.5</i>	<i>31.1</i>	<i>16.0</i>	<i>Bent to 98% without fracture 26/6/94</i>												
<i>Lower part</i>		<i>.86</i>	<i>"</i>	<i>.580</i>	<i>17.5</i>	<i>30.2</i>	<i>11.0</i>	<i>Bent to 92% without fracture 26/6/94</i>												
<i>Well hammered & examined with good results 21/6/94</i>																				
<i>Dropped and hammered with good results 13/6/94</i>																				
<i>Charles Cooper</i>																				
<i>Lloyd's Register Foundation</i>																				
<i>BE64-0127</i>																				

Bel 443

BEL 64-0127

No 113

Cast Steel Sliver Machine

Marmston Grange

Bel Rpt No 4443



© 2019

Lloyd's Register
Foundation