

THE STEEL COMPANY OF SCOTLAND, LIMITED.

Test Room Sheet

Newton

Works, the

5th day of February 1895

ORDER No.	QUALITY.	CHARGE No.	SAMPLE No.	SIZE OF SAMPLE.			BREAKING STRAIN.		EXTENSION.			CONDITION.		INITIAL ST.		SIZE OF FRACTURE.				REMARKS
				Bth.	Thk.	Area.	Actual Tons.	Per 100 Tons.	% Ins.	% Ins.	% Ins.	Long or Cross.	Annealed or Unannealed.	Actual Ton.	Per 100 Tons.	Bth.	Thk.	Area.	%	
<p>Rudder Stock for Meyers W. Man Clark & Co's N° 94</p> <p>.87 dia 594 13.4 30.9 21.0 Bent to 101° without fracture 25/1/95</p> <p>Dropped and hammered with good results 29/1/95</p> <p>Charles Cooper</p>																				

BEL 64 - 0218

Q4

basting (Steel)

Rudder Stock

Star of New Zealand

Reefast Rpt No. 44. 73.



© 2019

Lloyd's Register
Foundation