

THE STEEL COMPANY OF SCOTLAND, LIMITED.


Test Room Sheet

Newton

Works, the

4th day of July.

18 95

ORDER NO.	QUALITY.	CHARGE NO.	SAMPLE NO.	SIZE OF SAMPLE.			BREAKING STRAIN.		EXTENSION.			CONDITION.		INITIAL STRAIN.		SIZE OF FRACTURE.				REMARKS
				Bth.	Thk.	Area.	Actual Tons.	Per 8" Tons.	% Ins.	% Ins.	% Ins.	Long or Cross.	Annealed or Unannealed.	Actual Tons.	Per 8" Tons.	Bth.	Thk.	Area.	%	
<i>Rudder Frame for Messrs. Workman Clark & Co. No. 114</i>																				
<i>.88 diam. .608 19.0 31.2 18.5^{8 in.} Bent to 100° without fracture (2/7/95)</i>																				
																				
<i>Dropped and Hammered with good results 12/6/95</i>																				
<i>Robert Wright</i>																				

BEL 65-156



© 2019

Lloyd's Register Foundation