

THE STEEL COMPANY OF SCOTLAND, LIMITED.

Test Room Sheet

Newton

Works, the


4th day of July

1895

ORDER NO.	QUALITY.	CHARGE NO.	SAMPLE NO.	SIZE OF SAMPLE.			BREAKING STRAIN.		EXTENSION.			CONDITION.		INITIAL STRAIN.		SIZE OF FRACTURE.				REMARKS
				Bth.	Thk.	Area.	Actual Tons.	Per @ Tons.	% Ins.	% Ins.	% Ins.	Long or Cross.	Annealed or Unannealed.	Actual Tons.	Per @ Tons.	Bth.	Thk.	Area.	%	

Rudder Stock for Messrs. Workman Clark & Co. No. 114

8ⁱⁿ
 .85 diam. .567 18.5 32.6 19.0 Bent to 98° without fracture 4/7/95



Dropped and Hammered
 with good results 21/6/95

Robert Wright.



© 2019

Lloyd's Register
 Foundation

BE165 - 157

1124

Steel basting

% "Mourne"

Belfast Report No 4554



© 2019

Lloyd's Register
Foundation