


THE STEEL COMPANY OF SCOTLAND, LIMITED.

Test Room Sheet *Newton* Works, the *15th* day of *March* 18*95*

ORDER No.	QUALITY.	CHARGE No.	SAMPLE No.	SIZE OF SAMPLE.			BREAKING STRAIN.		EXTENSION.			CONDITION.		INITIAL STRAIN.		SIZE OF FRACTURE.				REMARKS.
				Bth.	Thk.	Area.	Actual Tons.	Per 8" Tons.	% 8 Ins.	% Ins.	% Ins.	Long or Cross.	Annealed or Unannealed.	Actual Tons.	Per 8" Tons.	Bth.	Thk.	Area.	%	

Store foot for Messrs Workman Clark & Co's N^o 114

.92 dia. .664 19.7 29.6 21.0 Bent through 90° without fracture 11/3/95



Dropped and hammered with good results 4/3/95

Charles Cooper

Bells - 169



© 2019

Lloyd's Register
Foundation

114

basting
stem

$\frac{1}{8}$ "Mourne"

~~Belfast Report No. 4584~~



© 2019

Lloyd's Register
Foundation