


# THE STEEL COMPANY OF SCOTLAND, LIMITED.

Test Room Sheet *Newton* Works, the *27<sup>th</sup>* day of *February* 18*95*

ORDER NO.	QUALITY.	CHARGE NO.	SAMPLE NO.	SIZE OF SAMPLE.			BREAKING STRAIN.		EXTENSION.			CONDITION.		INITIAL STRAIN.		SIZE OF FRACTURE.				REMARKS
				Bth.	Thk.	Area.	Actual Tons.	Per 8" Tons.	% 8 Ins.	% Ins.	% Ins.	Long or Cross.	Annealed or Unannealed.	Actual Tons.	Per 8" Tons.	Bth.	Thk.	Area.	%	
<i>Stern Frame for Messrs Workman Clark &amp; Co's N<sup>o</sup> 114</i>																				
<i>90 dia. 636 18.8 29.5 18.0 Bent through 100° without fracture 22/2/95</i>																				
																				
<i>Dropped and hammered with good result 12/2/95</i>																				
<i>Charles Coop.</i>																				

4841  
23/2/95  
BeGS-171



114

Stern Frame

of "Mourne" 2)

Belfast Report No 4554



© 2019

Lloyd's Register  
Foundation