


# THE STEEL COMPANY OF SCOTLAND, LIMITED.

Test Room Sheet *Newton* Works, the *23<sup>rd</sup>* day of *March* 18*95*

ORDER No.	QUALITY.	CHARGE No.	SAMPLE No.	SIZE OF SAMPLE.			BREAKING STRAIN.		EXTENSION.			CONDITION.		INITIAL STRAIN.		SIZE OF FRACTURE.				REMARKS.
				Bth.	Thk.	Area.	Actual Tons.	Per $\frac{3}{4}$ Tons.	% Ins.	% Ins.	% Ins.	Long or Cross.	Annealed or Unannealed.	Actual Tons.	Per $\frac{3}{4}$ Tons.	Bth.	Thk.	Area.	%	

*Shoe foot for Messrs Harland & Wolffs N<sup>o</sup> 297*

*.95 dia .708 22.3 31.5 16.0 Bent to 97° without fracture 21/3/95*



*Dropped and hammered with good results 18/3/95*

*Charles Cooper*

*4767  
22/3/95*



© 2019

Lloyd's Register  
Foundation  
BEL66-0130



"297" "Iran" Belfast Report

No. 4606

26th March 1995

Item

Boating

297



© 2019

Lloyd's Register  
Foundation