

# LLOYD'S REGISTER OF BRITISH AND FOREIGN SHIPPING.

## RESULTS OF TESTS OF STEEL.

Made by *Glasgow Iron & Steel Co. Lrskaid*

~~For~~ Results of tests from charges given on sheet from Belfast

	Test No.	Charge Mark.	Thick-ness.	Breadth.	Area.	Tons, Total.	Tons per square inch.	Extension in 8 ins. per cent.
		6626	Angle test only.					
Boiler tests		6620	.75	1.34	1.005	28.1	27.9	25
.		.	.91	1.06	.964	26.9	27.9	25
.		6629	.50	1.53	.765	21.0	27.4	28
.		-	.62	1.34	.830	22.4	27.0	25
Ship tests	7029	<del>7029</del>	.31	1.46	.452	13.1	29.0	21
.		-	.42	1.39	.583	18.6	31.9	25
Boiler tests		6590	.49	1.68	.822	22.6	27.5	28
.		6585	.70	1.89	1.323	36.9	27.8	30
.		.	.61	1.68	1.024	28.8	28.1	27
.		.	.51	-	.856	24.1	28.2	28
.		6586	.62	1.89	1.171	33.5	28.6	23
.		-	.43	1.49	.640	17.3	27.0	25
.		6820	.88	1.44	1.267	34.2	27.0	26
.		6642	.80	1.35	1.080	28.6	26.5	25
.		-	.80	1.03	.515	14.2	27.6	27

*A. B. Harris*

*10/4/10.*

*Stay bars made by Steel Co of Scotland*

*Bull Angles  
9" x 3"*

*S. 24*

*S. 24*

*S. 24*

*30.1 28*

*30.0 26*

*30.0 22*

*S. D. Cuthbert*

*10/4/10.*



BEL 71-105