

ORDER No.	QUALITY.	CHARGE No.	SAMPLE No.	SIZE OF SAMPLE.			BREAKING STRAIN.		EXTENSION.			CONDITION.		INITIAL STRAIN.		SIZE OF FRACTURE.				REMARKS
				Bth.	Thk.	Area.	Actual Tons.	Per $\square$ Tons.	% Ins.	% Ins.	% Ins.	Long or Cross.	Annealed or Unannealed.	Actual Tons.	Per $\square$ Tons.	Bth.	Thk.	Area.	%	
<p>Results of tensile &amp; bend tests made on Stern Frame (No 2) for Messrs. the Naval Construction &amp; Armaments Coy's Lim. Barrow No 218, manufactured by Messrs. the Ayrshire Steel Foundry Coy Lim. 8"</p> <p>1.53.50.765 22.4 29.2 22.5</p> <p>Bend test - bent as shown to 91° without fracture.</p> <p>Wm. H. Hiddell Surveyor to Lloyd's Register Glasgow</p>																				BRW 42-0108



© 2019

Lloyd's Register  
Foundation

BRW42-0108