

Steel & Coke
THE WEARDALE ~~IRON~~ & COAL COMPANY, LTD., TUDHOE IRON WORKS, SPENNYMOOR.
PARTICULARS OF TESTS MADE FROM "WEARDALE STEEL" (SIEMEN'S PROCESS).

Supplied to Messrs. J. A. Young & Son

Boiler Number _____ Order Received on 11th October 1888 Tested by _____ Completed on _____
 Do. _____ Do. _____ Do. _____ Do. _____
 Do. _____ Do. _____ Do. _____ Do. _____

A1/6189.

Dates of Testing.	Marks.	No. of Plates.	SIZE.	POSITIONS.	Plate No.	Plate cut into.	Tons per Square inch.	Elongation per cent. $\frac{8}{in.}$	Plate No.	Plate cut into.	Tons per Square inch.	Elongation per cent. $\frac{8}{in.}$	Plate No.	Plate cut into.	Tons per Square inch.	Elongation per cent. $\frac{8}{in.}$	Plate No.	Plate cut into.	Tons per Square inch.	Elongation per cent. $\frac{8}{in.}$	REMARKS.
		1	5' 0 $\frac{3}{4}$ " x 4' 0 $\frac{3}{4}$ "	Shell quality	6436A	1	26.4	27													
		1	4' 6 $\frac{1}{2}$ " . . .	"	"	1	26.4	27													
		2	12' 0" . 11 $\frac{1}{2}$ " $\frac{7}{8}$	"	6468F	1	28.3	26	6464	1	27.8	29									
		20	9 $\frac{1}{2}$ Dia. $\frac{7}{8}$	"	"	20	28.3	26													
		4	11 $\frac{1}{2}$ " . . 1 $\frac{1}{4}$ "	"	6546A	4	27.8	27													
		1	18" . . 1 $\frac{3}{8}$ "	"	6263D	1	28.3	29													
		1	17" . . .	"	"	1	28.3	29													
		2	19' 6" x 5' 0 $\frac{3}{4}$ " $\frac{7}{8}$	"	6467	1	27.7	30	6467B	1	28.5	28									
		2	19' 3 $\frac{1}{4}$ " . . .	"	6467C	1	27.3	30	6467D	1	29.4	26									



14th Sep^r 1903



© 2019
 Lloyd's Register
 Foundation
 CRK93-0363.1