


No. 8562

(Received at London Office,



TESTS OF BOILER STEEL.

Tests of 11 Steel plates manufactured by W. Beardmore & Co of Parkhead for Boiler No. to be constructed by Messrs Rowley Bros of Dunfermline for S. S. Flower.

Date first visit 6.4.88, last visit 8.9.88, No. of visits

The plates specified in the accompanying copy of Advice Notes were rolled from charges. The tensile test has been applied to samples as set forth below, and the temper and bending tests to a shearing from each plate with satisfactory results

When a second test is applied, the result should be recorded immediately below the record of the original test. The number of plates or bars included in a rejection must be clearly stated.

No.	Purpose.	Charge Mark.	No. of plates or bars in same charge	Mark on plate and test piece.	Dimensions.			Ultimate Stress.		Exten. in 8 ins.	Remarks.
					Thickn.	Brdth.	Area.	Total.	Sq. Inch.		
					Ins.	Ins.	Ins.	Tons.	Tons.	%	
1	7 1/2 Dia. x 1/16	V119			962.74	1.34	991	27.9	28.1	22	

Fee £ : :
 Expenses £ : :
 £ : : To be paid by

© 2019
 John T. Findlay Pro H. Hand
 Surveyor, Lloyd's Register,
 Glasgow. 8/9/88