

of test 12.5.97 Can each boiler be worked separately

Area of fire grate in each boiler

DALZELL STEEL AND IRON WORKS, OTHERWELL.

MAY 96

Messrs Babcock & Wilcox Ltd

Date, 7th May

GWT
8 MAY 1896

1896

ORDER No.	TEST No.	Description.	SIZES.			BREAKING STRESS.		ELONGATION PER CENT.		PLATE CUT INTO.	SIZE.
			Thickness.	Width.	Area.	Tons on Piece.	Tons per Sqr. Inch.	8 Inches.	10 Inches.		
B	8942	8430 Plate	51	1.88	.958	27.1	28.2	28.0	26.0	2	5.7 x 15 1/2 x 1/2
b	"	"	"	"	"	"	"	"	"	1	4.4 x 9 x 1/2
b	"	8293	"	4.5	2.25	1012	29.1	28.7	25.0	1	9.7 1/2 x 87 x 7/8
"	"	"	"	"	"	"	"	"	"	"	"

FOR DAVID COLVILLE & SONS LTD.

Edw. B. Allen

TESTING SURVEYOR.

J.W.
8 MAY 1896



D.R.T.
8 MAY 1896

Lloyd's Register Foundation

FAULT - 0066