

TESTS OF BOILER STEEL.

Tests of 3 Steel plates manufactured by Messrs. J. & W. Meadmore of Parkhead, Glasgow for Boiler No. 222 to be constructed by Messrs. J. & G. Thomson of Glasgow for Messrs. J. & G. Thomson's S.S. No. 222

Date first visit 14/5/84 last visit 16/5/84 No. of Visits 2

The plates specified in the accompanying copy of Advice Notes were rolled from charges. The tensile test has been applied to 1 samples as set forth below, and the temper and bending tests to a shearing from each plate, with satisfactory results.

When a second test is applied, the result should be recorded immediately below the record of the original test. The number of plates or bars included in a rejection must be clearly stated.

No.	Purpose.	Charge Mark.	No. of plates or bars in same charge	Mark on plate and test piece.	Dimensions.			Ultimate Stress.		Exten. in 8 ins.	Remarks.
					Thickn.	Brdth.	Area.	Total.	Sq. Inch.		
					Ins.	Ins.	Ins.	Tons.	Tons.		
1	18.4 x 8 1/2 x 5/16	D66		387	.95	1.07	1.016	28.83	28.3	31	

Fee £ : :

Expenses £ : :

£ : :

To be paid by Messrs. J. & W. Meadmore Glasgow 19/5/84

Surveyor, Lloyd's Register, W. Andrews

John Thomson
122



© 2021

Lloyd's Register
Foundation

REGISTER OF SHIPWRECKED SHIPS

REGISTER OF SHIPWRECKED SHIPS AND FOREIGN SHIPWRECKED