

Glasgow Report No. 4319 + 416

LLOYD'S REGISTER OF BRITISH AND FOREIGN SHIPPING

No. 2865.

(Received in London Office)



TESTS OF BOILER STEEL

Tests of 2 Steel Bars manufactured by Messrs D. Colville & Sons of Glasgow for Boilers Nos 399 & 400 to be constructed by Messrs R. Macfie & Sons of Glasgow for their S.S. No. 399 & 400

Date first visit July 7th 1885 last visit No. of visits

The specified in the accompanying copy of Advice Notes were rolled from charges. The tensile test has been applied to 1 sample as set forth below, and the temper and bending tests as required by Circular No. 438

When a second test is applied, the result should be recorded immediately below the record of the original test. The number of plates or bars included in a rejection must be clearly stated.

No.	Purpose.	Charge Mark.	No. of plates or bars in same charge	Mark on plate and test piece.	Dimensions.			Ultimate Stress.		Exten. in 8 ins.	Remarks.
					Thickn.	Brdth.	Area.	Total.	Sq. Inch.		
					Ins.	Ins.	Ins.	Tons.	Tons.	%	
1	Angle Bar 4 1/2 x 3 1/2 (388)			408	.485	1.09	528	14.31	27.1	25.0	

D.S.
28/8/85

Fee £ : :
Expenses £ : :
£ : :

To be paid by



© 2021
H. Moore
Surveyor, Lloyd's Register
Glasgow
26.8.85