

No. 3381.

LLOYD'S REGISTER OF BRITISH AND FOREIGN SHIPPING

(Received at London Office

NG.
RECEIVED
FEB. 86

Date first visit Feb 12 1886 last visit

No. of visits

The _____ specified in the accompanying copy of Advice Notes were rolled from _____ charges. The tensile test has been applied to _____ samples as set forth below, and the temper and bending tests to a shearing from the plate.

When a second test is applied, the result should be recorded immediately below the record of the original test. The number of plates or bars included in a rejection must be clearly stated.

No.	Purpose.	Charge Mark.	No. of plates or bars in same charge.	Mark on plate and test piece.	Dimensions.			Ultimate Stress.		Exten.	Remarks.
					Thickn.	Brdth.	Area.	Total.	Sq. Inch	in 8 ins.	
					Ins.	Ins.	Ins.	Tons.	Tons.	%	
1	18.10 x 7/2 x 1/8	4244		1872	1.13	1.18	1.333	39.45	29.5	25.5	
										<div style="text-align: center;"> <i>m</i> 25.2-96 </div>	

Fee £ :

Expenses £ : .

£ : :

To be paid by

[T. & SON-6000-5/5/85.]

Surveyor, Lloyd's Register.

Clayton
19.2.86

GLS205-0200