

TESTS OF BOILER STEEL.

Tests of *S* Steel plates manufactured by *The Steel Co. of Scotland of Glasgow*
for Boilers No. *253* to be constructed by *The London Glasgow & Co. of Glasgow*
for *the S.S. No. 253 building by the same firm*
Date first visit *22/9* last visit *26/9/87* No. of visits *2*
The _____ specified in the accompanying copy of Advice Notes were rolled from
charges. The tensile test has been applied to *4* samples as set forth below,
and the temper and bending tests *to a shearing taken from each*
plate, with satisfactory results.

When a second test is applied, the result should be recorded immediately below the record of the original test. The number of plates or bars included in a rejection must be clearly stated.

No.	Purpose.	Charge Mark.	No. of plates or bars in same charge.	Mark on plate and test piece.	Dimensions.			Ultimate Stress.		Exten. in 8 ins.	Remarks.
					Thickn.	Brdth.	Area.	Total.	Sq. Inch		
					Ins.	Ins.	Ins.	Tons.	Tons.	%	
<i>1</i>	<i>Shell Strap</i>	<i>C.259</i>		<i>8998</i>	<i>1.15</i>	<i>1.28</i>	<i>1.472</i>	<i>42.6</i>	<i>28.9</i>	<i>25.5</i>	<i>Annealed</i> <i>Cons. piece</i>
<i>2</i>	<i>Shell</i>	<i>J.264</i>		<i>9062</i>	<i>1.27</i>	<i>1.15</i>	<i>1.461</i>	<i>40.55</i>	<i>27.7</i>	<i>26.57</i>	
<i>3</i>				<i>"</i>	<i>1.27</i>	<i>1.00</i>	<i>1.27</i>	<i>34.15</i>	<i>26.8</i>	<i>24</i>	
<i>4</i>	<i>Tube plate or stock</i>			<i>9074</i>	<i>.92</i>	<i>1.15</i>	<i>1.058</i>	<i>28.3</i>	<i>26.7</i>	<i>27</i>	

Adt
29.9.87

Fee £ : :
Expenses £ : :
£ : :

To be paid by

The Lon. & Glob. Ins. Co.
No. 25-5-13



© 2021

Lloyd's Register
Foundation

THE LLOYD'S REGISTER OF BRITISH AND FOREIGN SHIPPING