

THE STEEL COMPANY OF SCOTLAND, LIMITED.

Test Room Sheet

Newton

Works, the

21st.

day of

February

1893

Test Room Sheet																				
ORDER NO.	QUALITY.	CHARGE NO.	SAMPLE NO.	SIZE OF SAMPLE.			BREAKING STRAIN.		EXTENSION.			CONDITION.		INITIAL STRAIN.		SIZE OF FRACTURE.				REMARKS.
				Bth.	Thk.	Area.	Actual Tons.	Per 8" Tons.	% Ins.	% Ins.	% Ins.	Long or Cross.	Annealed or Unannealed.	Actual Tons.	Per 8" Tons.	Bth.	Thk.	Area.	%	
Two Propeller Brackets & two Stern Lube Shields for Messrs. Barclay Curle & Co. No 383																				
8"																				
.92 Dias 664 20.2 30.4 23.0																				
All cast in one charge																				
<div><div>Band test bent as shown to 92° without fracture.</div><div>Alex. A. Kiddle Surveyor to Lloyd's Register Glasgow</div></div>																				

© 2021

Lloyd's Register Foundation

GLS232-0086



© 2021

Lloyd's Register Foundation

GLS232-0086