

THE STEEL COMPANY OF SCOTLAND, LIMITED.

Test Room Sheet *Newton* Works, the *21st* day of *August* 18*94*

ORDER No.	QUALITY.	CHARGE No.	SAMPLE No.	SIZE OF SAMPLE.			BREAKING STRAIN.		EXTENSION.			CONDITION.		INITIAL STRAIN.		SIZE OF FRACTURE.				REMARKS.
				Bth.	Thk.	Area.	Actual Tons.	Per 6" Tons.	%	%	%	Long or Cross.	Annealed or Unannealed.	Actual Tons.	Per 6" Tons.	Bth.	Thk.	Area.	%	
									8 Ins.	Ins.	Ins.									
<i>Propeller brackets for Messrs Barclay Curle & Co. N^o 393</i>																				
			<i>N^o 1</i>	<i>86</i>	<i>dia</i>	<i>580</i>	<i>18.1</i>	<i>31.2</i>	<i>11.5</i>	<i>Bent to 90° without fracture 21/8/94</i>										
			<i>N^o 2</i>	<i>89</i>	<i>"</i>	<i>622</i>	<i>19.8</i>	<i>31.8</i>	<i>20.0</i>	<i>"</i>	<i>" 96°</i>	<i>"</i>	<i>"</i>	<i>"</i>	<i>"</i>	<i>"</i>	<i>"</i>	<i>"</i>		
<div><div><i>N^o 1</i></div><div><i>N^o 2</i></div></div> <p><i>Dropped & hammered with good results 21/8/94</i></p> <p><i>Charles Cooper</i></p>																				

© 2021
Lloyd's Register
Foundation

GLS244-0120

© 2021

Lloyd's Register
Foundation

GLS244-0120