

Gls 13336

THE STEEL COMPANY OF SCOTLAND, LIMITED.

Test Room Sheet *Newton* Works, the *7th* day of *March* 18*94*

ORDER No.	QUALITY.	CHARGE No.	SAMPLE No.	SIZE OF SAMPLE.			BREAKING STRAIN.		EXTENSION.			CONDITION.		INITIAL STRAIN.		SIZE OF FRACTURE.				REMARKS.
				Bth.	Thk.	Area.	Actual Tons.	Per $\frac{1}{2}$ Tons.	% 8 Ins.	% Ins.	% Ins.	Long or Cross.	Annealed or Unannealed.	Actual Tons.	Per $\frac{1}{2}$ Tons.	Bth.	Thk.	Area.	%	
<p><i>Item Price for Messrs A. Stephen & Sons N^o 353</i></p> <p><i>.85 diai .567 16.6 29.2 23.0 Bent to 94% without fracture</i></p>																				
<p><i>Dropped & hammered with good results 24/2/94</i></p> <p><i>Charles Cooper</i></p>																				