

THE STEEL COMPANY OF SCOTLAND, LIMITED.

Test Room Sheet *Newton* Works, the *19th* day of *March* 18*95*

ORDER No.	QUALITY.	CHARGE No.	SAMPLE No.	SIZE OF SAMPLE.			BREAKING STRAIN.		EXTENSION.			CONDITION.		INITIAL STRAIN.		SIZE OF FRACTURE.				REMARKS.
				Bth.	Thk.	Area.	Actual Tons.	Per 2" Tons.	% Ins.	% Ins.	% Ins.	Long of Cross.	Annealed or Unannealed.	Actual Tons.	Per 2" Tons.	Bth.	Thk.	Area.	%	
<p><i>Stern frame for The Fairfield S. B. & Eng. Co^s Lm. N^o 386</i></p> <p><i>.95 dia. .708 23.6 33.3 17.0 Bent through 96° without fracture 7/3/95</i></p> <p><i>Hammered with good results 16/3/95.</i></p> <p><i>Charles Cooper</i></p>																				



© 2021

Lloyd's Register
Foundation

G65251-0093