

*Wm McCallan*

TESTS OF STEEL AT PARKHEAD FORGE ROLLING MILLS AND STEEL WORKS.

DATE.	CONSIGNEE.	Test No.	Tons per Square Inch.	Elongation per Cent.	No. of	SIZE.	REMARKS.
<i>1700</i> <i>April 6</i>				<i>8</i>			
<i>1</i>	<i>3" = 4088</i>	<i>262</i>	<i>30.</i>			<i>M<sup>r</sup> Common</i>	
<i>2</i>	<i>3" = 4088</i>	<i>31.9</i>	<i>20.</i>	<i>x</i>		<i>Lloyds</i>	
<i>3</i>	<i>17/8"</i>	<i>281</i>	<i>33.</i>				
<i>8</i> <i>4</i>	<i>17/8</i>						



© 2019

Lloyd's Register  
Foundation

GLS 288 - 009B.1