

TELEGRAMS:-  
"WEARDALE," SPENNYMOOR.



4775


Dec 22<sup>nd</sup> 1899.

# The Weardale Iron & Coal Company Ltd

## TESTING DEPARTMENT.

Surveyor's Advice of Tests made in Weardale Siemens' Steel Boiler Plates & Bars ordered by Messrs. *Central Marine Eng'rs* for their Boiler No. *R 88.* *Hartlepool*

Samples of Material specified in this Advice have been tested in my presence, and comply with Lloyd's requirements.



*Shells*

TENSILE 27 TO 32 TONS.

SURVEYOR TO LLOYD'S REGISTER.

DATE OF ORDER	NO	DIMENSIONS			CAST NO &c.
		LENGTH	BREADTH	THICKNESS	
9/12/99	5	94 1/2	10 1/2	5/8	2411 C B.S.
	2	16.9	30	1/2	2459 G C.S.
	2	15 1/3	29 1/2	1	2454 H —
	2	8 1/2	4 1/2	1	2415. 2444 E C.B.
	1	4 1/4	5 1/2	1	2410 E —
	2	4 1/2	4 1/2	15/32	2460 D G.C.
	32	2 1/4	1 1/4	1/2	2392 H.H. G.

46 Plates

*Llewellyn Grogan*

SURVEYOR TO LLOYD'S REGISTER  
WEST HARTLEPOOL.

20. XII. 99



© 2020

Lloyd's Register  
Foundation

HPL389-0187