

TELEGRAMS:-
"WEARDALE," SPENNYMOOR.



5306


Dec 15th 1899.

The Weardale Iron & Coal Company Ltd

TESTING DEPARTMENT.

Surveyor's Advice of Tests made in Weardale Siemens Steel
Boiler Plates & Bars ordered by Messrs Central Marine Eng Works
for their Boiler No. R 88 Hartlepool

Samples of Material specified in this Advice have been tested
in my presence, and comply with Lloyd's requirements.




TENSILE $\frac{26}{30}$ TO $\frac{30}{30}$ TONS

SURVEYOR TO LLOYD'S REGISTER.

DATE OF ORDER	No	DIMENSIONS			CAST No &c.
		LENGTH	BREADTH	THICKNESS	
9/12/99	2	5.3	4 1/4	5/8	2384A
	4	5.0	5 1/8	1	2384E
	4	4 1/4	4 1/2	3/32	2389C
	4 1/2	4 1/2	6.5 1/4	15/16	2360 1/2 A.
	1 1/2	8 1/16	2 1/8	3/32	2356 BB
	1 1/2	8 1/16	2 5/8	3/4	2390 CC
16	Plates				

16 Plates
L. E. M. Beggs



21. XII. 99

© 2020

Lloyd's Register
Foundation

HPL389-0188