

# Lloyd's Register of British and Foreign Shipping.

*5/6 Danube*  
(Report on Machinery, No. *8955* Port *Hull*)

## No. *1841* ENGINE FORGINGS OR CASTINGS.

I have to report that the ~~Iron or Steel Forgings or~~ Castings, as herein described, manufactured by *Messrs John Spencer & Sons* of *Newburn* for the Engines No. \_\_\_\_\_ being constructed by *Messrs G D Holman & Co* of *Hull* for the Ship No. \_\_\_\_\_, being built by \_\_\_\_\_ of \_\_\_\_\_ have been inspected by me as set forth below, and found to be, so far as can be seen, *sound*

The words FORGINGS or CASTINGS, IRON or STEEL, should be struck out as may be required.

Mark on Forgings.

Lloyd's  
No. *330778B*  
*JG*


*John C Craig*  
*Newcastle*

|                           | CRANK <sup><i>Wals</i></sup> SHAFT. | STRAIGHT SHAFTING. |                      |                  |
|---------------------------|-------------------------------------|--------------------|----------------------|------------------|
|                           |                                     | THRUST SHAFT.      | INTERMEDIATE SHAFTS. | PROPELLER SHAFT. |
| Material * ..             | <i>Siemens steel</i>                | /                  |                      |                  |
| How made ..               | <i>Cast</i>                         |                    |                      |                  |
| Dimensions ..             | _____                               |                    |                      |                  |
| Progress on Inspection .. | <i>Cast &amp; Tested</i>            |                    |                      |                  |
| Dates when Inspected ..   | <i>January 12 &amp; 22/94</i>       |                    |                      |                  |

PARTICULARS OF TESTS APPLIED TO CASTINGS:—

*One piece 8" long and 8" dia cut from each wheel was bent 90° without fracture*

| Forging No   | Eng No     | Ship No      |
|--------------|------------|--------------|
| <i>3307B</i> | <i>394</i> | <i>6 103</i> |
| <i>3308B</i> | <i>393</i> | <i>6 102</i> |



© 2019

Lloyd's Register Foundation

\* If of iron, state whether scrap or puddled iron. If of steel, state whether made on the Bessemer or the Siemens-Martin process.