

ANNUAL SURVEYS.

6279

No. Supp Survey held at London Date April 18 1840
 on the Ship Owen Glendower Master Tolman
 Tonnage 852 Built at London When built 1837
 By whom built Green & Wigram Owners Algreen
 Port belonging to London Destined Voyage Madras
 If Surveyed Afloat or in Dry Dock Blackwall Dock

Original Survey, No. 5458, Port of London 1839 Classed 12A1

The Surveyor is required to state the present Condition of the

Decks	Breasthooks	Capstan
Upper Deck Beams & Fastenings	Transoms	Pumps
Lower Deck Beams & Fastenings	Timbers of the Frame	Masts, Yards, &c.
Spirketting	Topsides	Sails
Plank Shears	Wales	Cables
Waterways	Plank and Treenails (Outside to the Water's Edge)	Anchors No. of
Hatchway Comings	Rudder	Standing & Running Rigging
	Windlass	Copper

General Observations and Opinion, The copper is good and perfectly smooth
as required by the Instructions,
In my opinion she is eligible to remain
as classed 12A1

Committee Minute 21st April 1840

Character assigned 12A1

George Bayley

No. Supp Survey held at London Date April 20th 1840
 on the Schooner Elizabeth Master Patie
 Tonnage Built at Perth When built 1840
 By whom built Owners
 Port belonging to Perth Destined Voyage
 If Surveyed Afloat or in Dry Dock Afloat at Scovells Wharf

Original Survey, No. 489 Port of Dundee Classed 5A1

The Surveyor is required to state the present Condition of the

Decks	Breasthooks	Capstan
Upper Deck Beams & Fastenings	Transoms	Pumps
Lower Deck Beams & Fastenings	Timbers of the Frame	Masts, Yards, &c.
Spirketting	Topsides	Sails
Plank Shears	Wales	Cables
Waterways	Plank and Treenails (Outside to the Water's Edge)	Anchors No. of
Hatchway Comings	Rudder	Standing & Running Rigging
	Windlass	Copper

General Observations and Opinion, In compliance with the directions of the Chairman of
as required by the Instructions, the Classification Committee I have been ordered to
submit specimens of Elm, Ash & Larch Timber used
in her keel &c. The Elm is of very good quality but similar
to that known on the East Coast by the name of Flemish

Committee Minute 21st April 1840

Character assigned 5A1

Elm which is somewhat more durable than
some other kinds of Elm - The ash presents
nothing different to good heavy ash suitable for
Coopers use. The larch is of the usual quality.

The materials are not so superior of their kind as to entitle them in my opinion to any longer term
than is allotted them in the table of materials
George Bayley