

copy

Hallside, the 14th day of November 1888

Test No	Piece No	Order No	Spec	Dimensions			Ultimate Stress		Extension			Remarks
				Bath	Thk	Area	On piece	Per sq in	Length	Ins	Per cent	
0	13H	6928	a	1.23	.51	.627	18.6	29.6	10		21.0	1 Angle bar 3" x 3" x 5"
1	14	"	"	1.20	.50	.600	17.7	29.5	"		26.0	
2	18	"	"	"	.55	.660	19.4	29.8	"		24.5	10 " " 5" x 4" x 1/2"
3	31	"	"	"	.48	.546	16.0	24.4	"		26.0	
4												1 Bar 5" x 3" x 1/2" Lee
5												

Tested in presence of Board of Trade Surveyor

Test results of material for
New East Ferry Rd & Co

pro Steel Co
J. H. Rutherford
Inspector

© 2021

M
21/11/88

Lloyd's Register
Foundation

LON724-0034