



(Received in London Office.

TESTS OF BOILER STEEL.

PPING.
Office,

The steel plates specified in the accompanying copy of Advice Notes were rolled from _____ charges. The tensile test has been applied to 4 samples as set forth below, and the temper and bending tests to a sample taken from each of the plates advised, all of which proved satisfactory.

No.	Purpose. <i>Dimensions</i>	Charge Mark.	No. of plates or bars in same charge	Mark on plate and test piece.	Dimensions.			Ultimate Stress.		Exten. in 8 ins. %	Remarks.
					Thickn.	Brdth.	Area.	Total.	Sq. Inch.		
					Ins.	Ins.	Ins.	Tons.	Tons.		
1.	$7\frac{1}{4} \times 5 \times \frac{1}{2}$	7282.	—	3406	502	1.725	865	23.79	27.5	24.5	
2.	$16.5 \frac{7}{8} \times 60 \frac{3}{4} \times \frac{3}{8}$	9288	—	2904	49	1.54	754	21.13	28.0	26.0	
3.	$5.5 \times 41 \times 6 \frac{1}{2} \times \frac{3}{4}$	C992	—	2938	752	1.537	1155	24.95	30.2	25.0	
4.	$9.0 \frac{1}{2} \times 38 \frac{7}{8} \times \frac{1}{2}$	B101	—	476	48	1.798	863	22.98	26.6	23.0	
<div style="text-align: center;"></div> <div style="text-align: right; margin-top: 100px;"><p>D-9. 15/4/84</p></div>											



© 2021

D. \$.

Fee	£	:	:
Expenses £	:	:	:
	£	:	:

To be paid by G. Colville & Co Glasgow. Surveyor, Lloyd's Register, 10/4/84

NWC 791-0100