


TESTS OF STEEL PLATES AT PARKHEAD FORGE ROLLING MILLS AND STEEL WORKS.

DATE.	No. of Test.	CONSIGNEE.	Quality.	DIMENSION OF TEST PIECE.			ULTIMATE STRESS.		ELONGATION.				TESTED BY	REMARKS.
				BREADTH.	Thick- ness.	Area.	Total.	Per Sq. In.	In. 8 In.	Per Cent.	In 10 In.	Per Cent.		
1890			Q/s											Charles Bends good
Nov 14 th	1496	Grangemouth Co.		1.16	.4	464	13.7	28.5		26			M ^r Roberts	R 277
21 st	1397	141		1.14	.35	399	12.1	30.2		22.			M ^r Edward	A 158
24 th	1545	"		1.09	.3	327	9.7	29.6		22.			"	W 308

Tests on ship plates supplied for
Grangemouth Dockyard Co's cl^d 141.

WILLIAM BEARDMORE & CO.

P. J. Biella



© 2021

Lloyd's Register
Foundation

SLD1018-0208

Lloyds Surveyors