

Appl:

LLOYD'S REGISTER OF BRITISH AND FOREIGN SHIPPING.

(Received in London Office

Date first visit 26/10/83 last visit 29/10/83 No. of Visits 2

The plates specified in the accompanying copy of Advice Notes were rolled from charges. The tensile test has been applied to 3 samples as set forth below, and the temper and bending tests to samples representative of each plate advised, all of which proved satisfactory.

No.	Purpose.	Charge Mark.	No. of plates or bars in same charge	Mark on plate and test piece.	Dimensions.			Ultimate Stress.		Exten. in 8 ins.	Remarks.
					Thickn.	Brdth.	Area.	Total.	Sq. Inch.		
1	$2.11\frac{1}{4} \times 11 \times \frac{3}{4}$	G184		3541	.78	1.252	.976	27.08	27.7	27.5	M10/11/83
2	$8.6 \times 34 \times \frac{1}{2}$	C881		3669	.487	1.252	.609	17.18	28.2	23.5	
3	$7.11 \times 83 \times \frac{9}{16}$	E524		3914	.548	1.64	.898	23.89	26.6	29.0	

Am. 10/11/83

When a second test is applied, the result should be recorded immediately below the record of the original test. The number of plates or bars included in a refection must be clearly stated.

Expenses £ : :

£ : :

To be paid by

Surveyor, Lloyd's Register,

[6000-18/6/81]

SLD948-0107

© 2021

Chas. Edwards
Surveyor, Lloyd's Register,
Lancaster Glasgow
8/4/53