


No. 2914.

(Received at London Office)



TESTS OF BOILER STEEL.

Tests of 1 Steel Plate manufactured by Messrs J Colville & Sons of Motherwell for Boiler No. 337 to be constructed by The North Eastern M.E.C. Sunderland for

Date first visit — last visit — No. of visits —

The — specified in the accompanying copy of Advice Notes were rolled from charges. The tensile test has been applied to 1 samples as set forth below, and the temper and bending tests as required by Circular No. 438

When a second test is applied, the result should be recorded immediately below the record of the original test. The number of plates or bars included in a rejection must be clearly stated.

No.	Purpose.	Charge Mark.	No. of plates or bars in same charge.	Mark on plate and test piece.	Dimensions.			Ultimate Stress.		Extens. in 8 ins.	Remarks.
					Thickn.	Brlth.	Area.	Total.	Sq. Inch		
					Ins.	Ins.	Ins.	Tons.	Tons.	%	
1	4' 4" x 32 1/2" x 1/2"	L691		7/34	5.2	1.65	.858	23	26.8	30.5	

D.F.
16/9/85.

Fee £ : :
Expenses £ : :
£ : :

To be paid by

© 2021
George Harrison
Surveyor, Lloyd's Register
Glasgow
Foundation

14-9-85