

No. 3215.

(Received in London Office)

Shipping Office
RECEIVED
71 JAN. 86
Hetherwell

Date first visit *Dec 15th 1885* last visit *.....* No. of visits *.....*

The _____ specified in the accompanying copy of Advice Notes were rolled from _____ charges. The tensile test has been applied to _____ samples as set forth below, and the temper and bending tests as required by Circular N° 420.

No.	Purpose.	Charge Mark.	No. of plates or bars in same charge	Mark on plate and test piece.	Dimensions.			Ultimate Stress.		Exten. in 8 ins. %	Remarks.
					Thickn.	Brdth.	Area.	Total.	Sq. Inch.		
					Inch.	Inch.	Sq. Inch.	Tons.	Tons.		
1	$1\frac{1}{4} \times 59 + \frac{5}{16}$	2139		2506	.92	1.42	1.306	38.05	29.1	27.5	JMC 1/1/86

To be paid by

Surveyor, Lloyd's Register,

Glasgow
8.1.86