

S. S. Kathleen Eld. report No 14658

(Received in London Office

-1 JAN. 86

Date first visit Nov. 21st last visit No. of visits

The _____ specified in the accompanying copy of Advice Notes were rolled from _____ charges. The tensile test has been applied to _____ samples as set forth below, and the temper and bending tests as required by Circular No. 438.

No.	Purpose.	Charge Mark.	N ^o . of plates or bars in same charge	Mark on plate and test piece.	Dimensions.			Ultimate Stress.		Exten. in 8 ins.	Remarks.
					Thickn.	Brdth.	Area.	Total.	Sq. Inch.	%	
					Inch.	Inch.	Sq. In.	Tons.	Tons.	%	
1	7.0 x 56 x 69 Sp - 3/4	L675		4242	72	1.25	.90	25.4	28.2	22.0	D.S. 11/1/85

Fee £ ; ;

Expenses £ : :

£ : :

To be paid by

Surveyor, Lloyd's Register

Glasgow
130.12.85

[T. & SON-6000 -5/5/85.]

SLD958-0043