

TESTS OF BOILER STEEL.

Date first visit Oct 20<sup>th</sup> 1885 last visit \_\_\_\_\_ No. of visits \_\_\_\_\_

The \_\_\_\_\_ specified in the accompanying copy of Advice Notes were rolled from \_\_\_\_\_ charges. The tensile test has been applied to \_\_\_\_\_ sample, as set forth below, and the temper and bending tests as required by Circular No. 48.

No.	Purpose.	Charge Mark.	No. of plates or bars in same charge.	Mark on plate and test piece.	Dimensions.			Ultimate Stress.		Exten. in 8 ins.	Remarks.
					Thickn.	Brdth.	Area.	Total.	Sq. Inch		
					Ins.	Ins.	Ins.	Tons.	Tons.	%	
1	10 1/4 x 3 1/2 x 28 x 24 x 1/16	J528		4150	.58	129	.748	21.05	28.1	26.5	

D.F.  
30/10/85

© 2021

<i>Fee</i> . . . . .	£	:	:
<i>Expenses</i> £	:	:	
	£	:	:

*To be paid by*

[T. & SON-6000-5/5/85.]

SLD958-0044

© 2021  
Lloyd's Register  
Foundation

D. G.  
30/10/88

H. Moore

Surveyor, Lloyd's Register.

Clayton

28.10.83