

TEST RESULTS FROM FORGINGS MADE BY MESSRS. T. FIRTH &
 SONS LTD., SHEFFIELD, FOR MESSRS. HARLAND & WOLFF'S G O /45.

Test No.	Lloyds No.	Description.	Tensile Tons per sq. inch.	Elong. on 3".	Bends.
42 A B	1607	Pro. Shaft	31.4	32.0	180
" T	"	"	31.6	31.0	"
43 A B	1608	Pro. Shaft	31.4	32.0.	"
" T	"	"	31.6	32.0	"
20 A B	1695	Inter. Shaft	32.0	33.0	"
" T	"	"	32.0	33.0	"
38 A B	1696	Inter. Shaft	32.0	29.0	"
" T	"	"	31.6	30.0	"
9 A B	1744	Inter. Shaft	30.6	30.0	"
" T	"	"	30.2	33.0	"
7 A B	1725	Inter. Shaft	31.8	30.0	"
" T	"	"	31.8	29.0	"
7 A	1734	Thrust Shaft.	30.6	32.0	"
A1	1735	Thrust Shaft	30.8	34.0	"
4 A B	1747	Inter. Shaft	30.8	30.0	"
" T	"	"	30.6	34.0	"
5 A B	781	Inter. Shaft	31.0	31.0	"
" T	"	"	31.4	32.0	"
8 A B	782	Inter. Shaft	31.6	30.0	"
" T	"	"	31.6	34.0	"
7 A B	783	Inter. Shaft	30.4	35.0	"
" T	"	"	29.8	34.0	"
8 A B	784	Inter. Shaft	31.8	32.0	"
" T	"	"	31.2	32.0	"
9 A B	780	Inter. Shaft	31.6	32.0	"
" T	"	"	29.6	31.0	"
3 A B	1819	Pro. Shaft	30.6	28.0	"
" T	"	"	30.4	34.0	"

(Signed) J. PRINGLE.
 Surveyor

to Lloyd's Register, Sheffield
 12.3.18.

© 2020

Lloyd's Register
 Foundation