

Lloyd's Register of Shipping.

(Report on Machinery, No. 93528 Port Truce)


No. 1406 ENGINE ~~FORGINGS OR~~ CASTINGS.

I have to report that the ~~Forgings or~~ Castings, as herein described, manufactured by Wm. Douglas & Co. of Warrand in Tyne for the Engines No. 919 being constructed by Warrand Shipway & Co. Ltd. of Warrand in Tyne for the Ship No. _____, being built by _____ of _____ have been inspected by me as set forth below, and found to be, so far as can be seen, sound and free from defects. These have been despatched to Warrand

Mark on ~~Forgings or~~ Castings.

Lloyd's
No. 1406
LR 13-11-35

- 2- Water Gauge Steels 11012
- 2- 1/2" Scot Bolts 53-54
- 3 Dead pins - 63-64-65
- 2 Tie pins 65-66



	CRANK SHAFT.	THRUST SHAFT.	INTERMEDIATE SHAFT.	TUBE SHAFT.
	FLYWHEEL SHAFT.			SCREW SHAFT.
Material* ...	Best Steel - beddie furnace process			
How made ...	Cast			
If Annealed ...	Yes			
Dimensions, Forgings				
Weight, Castings	5-3-14			
Progress on Inspection	Rough castings only			
Tests on Standard Test Pieces.				
Tensile Test— Tons per square inch	29.0			
Extension per cent	35.0			
Cold Bending Test— Angle before fracture	120°			
Dates when Inspected	13-11-35			

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

Fee (if any chargeable) £ To be paid at _____

* If of wrought iron, state whether piled bars or scrap. If of steel, state whether made by the Open Hearth process.

