

SHIP'S NAME

SANTO MARU

REPORT

Pha No. 230

THICKNESSES OF PLATING ascertained by drilling, and comparison of same with the original thicknesses.

The thicknesses are in hundredths of an inch.

NO.	AMIDSHIP.					FORWARD.					AFT.					REMARKS.
	Original Thickness	Thickness by drilling.		Diminution if any.		Original Thickness.	Thickness by drilling.		Diminution if any.		Original Thickness.	Thickness by drilling.		Diminution if any.		
		Port.	Std.	Port.	Std.		Port.	Std.	Port.	Std.		Port.	Std.	Port.	Std.	
DECK	50															
RAKE	H 57	56	50	1	2	58	53	44	5	14	60	56	55	4	5	
below	G 57	53	56	4	1	48	47	47	1	1	56	47	47	9	9	⊗ Renewed.
	F 57	50	(37)	7	-	47	37	44	10	3	50	41	50	9	-	
	E 57	50	(32)	7	-	48	44	44	4	4	52	50	49	2	3	
	D 57	53	56	4	1	47	37	50	10	-	50	50	50	-	-	
	C 57	56	56	1	1	52	42	56	10	-	STEALER			-	-	
	B 57	59	53	-	4	54	50	59	4	-	STEALER			-	-	
	A 57	44	50	13	7	STEALER			-	-	52	50	50	2	2	
KEEL	66	68		-		62	59		3		62	59		3		

Drillings at ends to be made in the vicinity of the peak bulkheads.

© 2020

Lloyd's Register  
Foundation

W1028-0034