

NAME

"LEANDROS"

Report Msl.

4-MAR 1949

No. 10745

KNESSES OF PLATING ascertained by drilling, and comparison of same with the original thicknesses.

The thicknesses are in  $\frac{m}{m}$  of an inch.

SURFACE	AMIDSHIP.					FORWARD.					AFT.					REMARKS.	
	Original Thickness.	Thickness by drilling.		Diminution if any.		Original Thickness.	Thickness by drilling.		Diminution if any.		Original Thickness.	Thickness by drilling.		Diminution if any.			
		Port.	Std.	Port.	Std.		Port.	Std.	Port.	Std.		Port.	Std.	Port.	Std.		Port.
H	10.2	10	10	0.2	0.2												
G	15.2	15	14	0.2	1.2	11.4	12	10	✓	1.4	11.4	X	X				
F	10.2	9	9	1.2	1.2	9.0	9	8	✓	1.0	9.0	9	8	✓	1.0		
E	11.4	8.5	11	2.9	0.1	9.0	④	8.5	✗	0.5	9.0	8	7	1.0	2.0	④ ✗ DOUBLING NOW FITTED	
D	11.4	9	10	2.5	1.5	9.0	10	⑤	✓	✗	9.0	8.5	8	0.5	1.0	⑤ ✗ OVER LOCAL WASTAGE	
C	12.7	9.5	X	3.2	✗	10.2	10	9	0.2	1.2	10.2	9.5	X	0.7	✗	X	DRILLING OMITTED
B	11.4	10	11.0	1.4	0.4	10.2	9	10	1.2	0.2	10.2	9	10	1.2	0.2		
A	12.7	11	10.5	1.7	1.2	11.4	9	13	2.4	✓	11.4	9	11	2.4	0.4		

Drillings at ends to be made in the vicinity of the peak bulkheads.

Pierre FONDEUR

W1035-0245

Lloyd's Register  
Foundation