

Rpt. 8.

For the information of Surveyors and the Committee only.

Received at

Office

10 JAN 1930

## Lloyd's Register of Shipping.

(Report on Vessel No.

9129

Port

Trieste

No. 3373.

## SHIP FORGINGS OR CASTINGS.

I have to report that the undermentioned ~~Iron or Steel Forgings or Castings~~, manufactured by Messrs ~~the Springfield Steel Co. Ltd.~~ of ~~Glasgow~~, for the Vessel No. 223, being built by Messrs ~~Carline Navale Frisino~~ of ~~Trieste~~ have been inspected by me as set forth below and found to be, so far as can be seen, ~~Sound~~.

~~Castings~~ despatched to Messrs John Hastie & Co. Ltd. Greenock.


Mark on Forgings or Castings.

Lloyd's

No. 3373.

L.E.L. 28.12.29.


One Tiller



	STERN FRAME.	RUDDER FRAME.	STEM.
Material* ...	Siemens-Martin Acid Open Hearth Steel		
How made ...	Cast		
If annealed ...	Annealed.		
Dimensions ...	To pattern		
Progress on Inspection ...	Rough dressed.		
Date when Inspected ...	5/12/29 - 28/12/29.		
CASTINGS.			
Tests on Standard Test Pieces.	Test No. 80		
Tensile Test—	31.2		
Tons per square inch	32.0%		
Extension per cent. ...	120° W.F.		
Cold Bending Test—	10 feet		
Angle before fracture	Yes.		
Drop Test—			
Height from ground ...			
Hammering Test—			
If made according to Rules / and found satisfactory ...			

SKETCHES OF FRAMES SHOWING POSITION AND DESCRIPTION OF WELDS OF FORGINGS.

Cub. ft. 16.  
13. 3. 14.



Fee (if any chargeable) £ — : 10 : 6 —

To be paid at GLASGOW

9 - JAN 1930

© 2021

\* If of Iron, state whether scrap or puddled Iron. If of Steel, state whether made on the Open Hearth process.  
2m. 1.26. T.

W1048-0024

Low for  
guide

Starting Air Receivers, No. 36

Total cubic capacity

{ 20 & 500 LIT.  
16 & 300 "

Internal diameter

{ 20 & 315 mm  
16 & 400 "

thickness

{ 14"  
17 "

Working pressure by Rules