

hellplating drilled and considered satisfactory. Drilling sheet attached

IE "CHELOHSIN"

Report Vancouver, No. 7780

B.C.

THICKNESSES OF PLATING ascertained by drilling, and comparison of same with the original thicknesses.

The thicknesses are in $\frac{1}{40}$ of an inch.

AMIDSHIP.						FORWARD.				AFT.				REMARKS.	
Original Thickness.	Thickness by drilling.		Diminution if any.		Original Thickness.	Thickness by drilling.		Diminution if any.		Original Thickness.	Thickness by drilling.		Diminution if any.		
	Port.	Std.	Port.	Std.		Port.	Std.	Port.	Std.		Port.	Std.	Port.		Std.
J	10	10	10	-	-	8	10	10	-	-	-	-	-	-	The Owners have made
H	10	10	10	-	-	8	11	12	-	-	-	-	-	-	a practice of fitting
G	14	13	13	1	1	10	14	12.5	-	-	10	10	10	-	heavier plates than
F	13	15	10.5	-	.25	11	12.5	12.5	-	-	11	12.5	10	-	1 original when renewing
E	13	10	12.5	3	.5	11	16	15	-	-	11	11	11	-	for wear & tear or
D	14	16	15	-	-	11	stealer		11	14	11	-	-	-	damage.
C	14	16	16	-	-	12	doubled		12	14	14	-	-	-	
B	14	13	12.5	1	.5	12	17	17	-	-	12	14	14	-	
A	14	13	13	1	1	12	17	17	-	-	12	14	16	-	
1	20	20	-	-	-	18	cement		18	cement		-	-	-	

Drillings at ends to be made in the vicinity of the peak bulkheads.

© 2020
 Lloyd's Register
 Foundation
 7/1/49
 W1067-0019