

SSEL'S NAME **CHELOHSIN**

Report **4745**

No. **Jan 25. 39**

THICKNESSES OF PLATING ascertained by drilling, and comparison of same with the original thicknesses.

The thicknesses are in **40** of an inch.

STRAKE.	AMIDSHIP.				FORWARD.				AFT.				REMARKS.
	Original Thickness.	Thickness by drilling.		Diminution if any.	Original Thickness.	Thickness by drilling.		Diminution if any.	Original Thickness.	Thickness by drilling.		Diminution if any.	
		Port.	Std.			Port.	Std.			Port.	Std.		
R SHEER STRAKE	10	10	9	1	8	8	9		8	8	9		
ke below.....	10	10	9	1	9	9	8		9	8	8		
N SHEER STRAKE	14	13	13	1 1	10	11	10		10	10	11		
Strake below F	13	13	13	new	11	14	14		11	12	10		1
" " E	13	13	13	new	18	18	18		11	12	12		
" " D	14	14	14		11	12	14		11	12	12		
" " C	14	13	13	1 1	12	12	12	. .	12	12	12	. .	
" " B	14	13	13	1 1	12	11	11	1 1	12	13	13	new	
" " A	14	14	14	. .	12	16	18		12	13	13	new	
" " new	20	20	20	. .	18	19	18	. .	19	19	18	new.	

*plates attached
with sheet*

© 2020

Drillings at ends to be made in the vicinity of the peak bulkheads.

Lloyd's Register
Foundation
Adapt
W1067-0032