

pt. 6.

For the information of Surveyors and the Committee only.

Received at \_\_\_\_\_

Office \_\_\_\_\_

19

**Lloyd's Register of Shipping.**

(Report on Vessel No. \_\_\_\_\_ Port \_\_\_\_\_)

**No. 4462-63. SHIP FORGINGS OR CASTINGS.**

I have to report that the undermentioned ~~Iron or Steel Forgings or Castings~~, manufactured by **Messrs. A.-B. Bofors** of **Bofors** for the Vessel No. **VIRGILIO** being built by \_\_\_\_\_ of \_\_\_\_\_ have been inspected by me as set forth below and found to be, so far as can be seen, **sound and free from defects.**

Mark on Forgings or Castings.

**Lloyd's****No. 4462-63****LR GA 4.3.27.****Gothenburg, 15th March, 1927.****1 Welin davit frame. 1 Welin davit arm.**


	<b>STERN FRAME.</b>	<b>RUDDER FRAME.</b>	<b>STEM.</b>
Material* ...	<b>S.M. Steel.</b>	<b>S.M. Steel.</b>	
How made ...	<b>Casted.</b>	<b>Casted.</b>	
If annealed ...	<b>Yes.</b>	<b>Yes.</b>	
Dimensions ...	<b>---</b>	<b>---</b>	
Progress on Inspection ...	<b>Finished.</b>	<b>Finished.</b>	
Date when Inspected ...	<b>4.3.27.</b>	<b>4.3.27.</b>	
<b>CASTINGS.</b>			
Tests on Standard Test Pieces.			
Tensile Test—			
Tons per square inch <i>m/n</i>	<b>48.5</b>	<b>48.2</b>	
Extension per cent. ...	<b>34.4</b>	<b>38.0</b>	
Cold Bending Test—			
Angle before fracture ...	<b>120° good.</b>	<b>120° good.</b>	
Drop Test—			
Height from ground ...	<b>---</b>	<b>---</b>	
Hammering Test—			
If made according to Rules and found satisfactory ...	<b>Good.</b>	<b>Good.</b>	

SKETCHES OF FRAMES SHOWING POSITION AND DESCRIPTION OF WELDS OF FORGINGS.

Fee (if any chargeable) £ **---** :To be paid at **Gothenburg.**

\* If of Iron, state whether scrap or puddled Iron. If of Steel, state whether made on the Open Hearth process.

2m.1.26. T.



© 2020

Lloyd's Register Foundation

W1069-0122

1953

Starting at \_\_\_\_\_ **RIVETED** Material **STEEL** Range of tensile strength **44/50.5 Kgs.** Working pressure \_\_\_\_\_