

For the information of Surveyors and the Committee only.

Received at \_\_\_\_\_ Office \_\_\_\_\_ 19 \_\_\_\_\_

# Lloyd's Register of Shipping.

(Report on Vessel No. \_\_\_\_\_ Port \_\_\_\_\_)

No. **4464-65** **SHIP FORGINGS OR CASTINGS.**

I have to report that the undermentioned ~~Iron or Steel Forgings or~~  
Castings, manufactured by **Messrs. A.-B. Bofors**  
of **Bofors** for the Vessel No. **VIRGILIO** being built  
by \_\_\_\_\_ of \_\_\_\_\_  
have been inspected by me as set forth below and found to be, so far as can  
be seen, **sound and free from defects.**

n Forgings or Castings.

Lloyd's

**Gothenburg, 15th March, 1927,**

No. **4464-65.**

LR GA 4.3.27.

**1 Welin davit frame. 1 Welin davit arm.**

*G. Brander*

	STERN FRAME.	RUDDER FRAME.	STEM.
Material	<b>S.M. Steel.</b>	<b>S.M. Steel.</b>	
Made	<b>Casted.</b>	<b>Casted.</b>	
Reheated	<b>Yes.</b>	<b>Yes.</b>	
Dimensions	<b>---</b>	<b>---</b>	
Process on Inspection	<b>Finished.</b>	<b>Finished.</b>	
When Inspected	<b>4.3.27.</b>	<b>4.3.27.</b>	
<b>CASTINGS.</b>			
Tests on Standard Test Pieces.			
Tensile Test—			
per square inch	<b>49.5</b>	<b>47.6</b>	
	<b>35.4</b>	<b>39.4</b>	
Extension per cent.			
Bending Test—			
angle before fracture	<b>120° good.</b>	<b>120° good.</b>	
Test—			
eight from ground	<b>---</b>	<b>---</b>	
merging Test—			
made according to Rules and found satisfactory	<b>Good.</b>	<b>Good.</b>	


SKETCHES OF FRAMES SHOWING POSITION AND DESCRIPTION OF WELDS OF FORGINGS.

Fee (if any chargeable) £ **---**

To be paid at **GOTHENBURG.**

If of Iron, state whether scrap or puddled Iron. If of Steel, state whether made on the Open Hearth process.

128. T.



© 2020

Lloyd's Register Foundation

W1069-0120

W1069-0120

Working pr

Starting at

Steel

Range of tensile strength

44/50.5 Kgs

Working pr