

THICKNESSES OF PLATING ascertained by drilling and comparison of same with the original thicknesses.

SEL'S NAME WAHINE

Report Wgtn. No. 4966

THICKNESSES OF PLATING ascertained by drilling, and comparison of same with the original thicknesses.

The thicknesses are in 100ths of an inch.

STRAKE.	AMIDSHIP.						FORWARD.						AFT.						REMARKS.
	Original Thickness.	Thickness by drilling.		Diminution if any.		Original Thickness.	Thickness by drilling.		Diminution if any.		Original Thickness.	Thickness by drilling.		Diminution if any.					
		Port.	Std.	Port.	Std.		Port.	Std.	Port.	Std.		Port.	Std.	Port.	Std.				
SHEER STRAKE																			
Below																			
SHEER STRAKE N.....	58	60	56		02	40	44	45	07			40	45	47					
Strake below M.....	56	56	56			40	43	43	09			40	44	44					
" " L.....	56	56	56			40	41	42				40	40	42					
" " K.....	56	60	55		01	40	47	50				40	42	42					
" " J.....	56	48	52	08	08	40	44	44				40	40	41					
" " H.....	56	55	43	01	13	40	44	44				40	48	47					
" " G.....	64	58	54	06	10	40	28	44	12			40	38	42	02				
" " F.....	64	56	54	08	10	40	36	44	04			40	45	33		04			
" " E.....	64	46	44	18	20	40	39	38	01	02		40	42	43					
" " D.....												40	42	41					

© 2019

W. K. M. R. S. Registrar

Drillings at ends to be made in the vicinity of the peak bulkheads.

SEL'S NAME WAHINE

Report Wgtn. No. 4966

© 2019

Wahine Foundation
Hoyd's Register

W1076-0102