

80 64

40

40

COPY

EL'S NAME

WAHINE

Report

Wght.

No.

THICKNESSES OF PLATING ascertained by drilling, and comparison of same with the original thicknesses.

The thicknesses are in of an inch.

STRAKE.	AMIDSHIP.						FORWARD.						AFT.						REMARKS.
	Original Thickness.	Thickness by drilling.		Diminution if any.		Original Thickness.	Thickness by drilling.		Diminution if any.		Original Thickness.	Thickness by drilling.		Diminution if any.					
		Port.	Std.	Port.	Std.		Port.	Std.	Port.	Std.		Port.	Std.	Port.	Std.				
SHEER STRAKE .....																			
below .....																			
SHEER STRAKE N .....	58	60	56	-	02	40	44	46	-	-	40	45	47	-	-				
M .....	56	56	56	-	-	40	43	45	07	-	40	44	44	-	-				
ake below .....						40	43	45	09	-	40	44	44	-	-				
L .....	56	56	56	-	-	40	41	42	-	-	40	40	42	-	-				
K .....	56	60	55	-	01	40	47	50	-	-	40	42	42	-	-				
J .....	56	48	48	08	08	40	44	44	-	-	40	40	41	-	-				
H .....	56	55	43	01	13	40	44	44	-	-	40	48	47	-	-				
G .....	64	58	54	06	10	40	28	44	12	-	40	38	42	02	-				
F .....	64	56	54	08	10	40	44	44	04	-	40	45	33	-	07				
E .....	64	46	44	18	20	40	39	38	01	02	40	42	43	-	-				
D .....											40	42	41	-	-				

Drillings at ends to be made in the vicinity of the peak bulkheads.

General Observations, Opinion as to Class, Recommendation, &amp;c.:—

W1076-0105

© 2019

Lloyd's Register  
Foundation