

LLOYDS' SURVEYORS ADVICE NOTE FOR BOILER MATERIAL.

TELEGRAPHIC ADDRESS, "COLVILLE," MOTHERWELL.
ALSO "COLVILLE," LONDON.

Palzell Steel & Iron Works.

Motherwell, 30th April 1912
 Messrs Babcock & Wilcox Ltd
 Glasgow
 Bought of DAVID COLVILLE & SONS,
 DALZELL (LIMITED.)

STEEL
by
OPEN HEARTH PROCESS.

BOILER STEEL BRANDED SHIP STEEL BRANDED

DALZELL
STEEL

ON ADMIRALTY AND WAR OFFICE LISTS
CONTRACTORS TO
BRITISH, COLONIAL AND FOREIGN GOVERNMENTS

Iron Branded "DAZZEL" with the Distinguishing Quality

ALL STEEL TESTED BEFORE LEAVING THE WORKS. IRON WHEN REQUIRED OF A SPECIFIED STRENGTH & DUCTILITY ALSO TESTED BEFORE BEING DESPATCHED.

Brand

Batch
N^o in

59551. $\frac{1}{63} = 2$ $\frac{2}{18} = 16$

[Page 150]

DALZELL
STEEL

To

Marine Dept.

Родился

Date & N ^o of Order	Marks	N ^o of	Length	Breadth	Thick ^s	Tons	Cwts	Qrs	Lbs	Numbers stamped on Material.
50 P38 137	50 20939/MB Cr. Plate	6	14 10 1/2	7 1/2	12"	19	16			2896 ✓
		1	14 3/4	-	"	18	20			2896 ✓
		8	14 7 1/2	7 1/2	7 1/2	12	2			8/✓329 ✓
		8	14 0 1/2	-	"	11	12 1/2			8/✓329 ✓
		<u>18</u>								<u>31 24</u>
		S =	24		28 ✓					
TENSILE STRENGTH	Other		26	TO	30 ✓	TONS				

L. Napier 1919
SURVEYOR LLOYD'S REGISTER

TENSILE STRENGTH *Other* 26 TO 30 TONS

SURVEYOR LLOYDS' REGISTER

Min Ext. 23% in 8"

2nd May 1942