

PAIRS. OR EXAMINATION AS PER RULE, FOR Special Survey.

NAME INCHCRAIG REPORT HONG KONG No. 9419

THICKNESSES OF PLATING ascertained by drilling, and comparison of same with the original thicknesses.

The thicknesses are in hundredths of an inch.

NAME.		AMIDSHIP.					FORWARD.					AFT.					REMARKS.	
		Original Thickness.	Thickness by drilling.		Diminution if any.		Original Thickness.	Thickness by drilling.		Diminution if any.		Original Thickness.	Thickness by drilling.		Diminution if any.			
			Port.	Std.	Port.	Std.		Port.	Std.	Port.	Std.		Port.	Std.	Port.	Std.		
HEER	K	.54	.20	.52	.34	.02	.40	.40	.40			.36	.40	.40				
	J	.58	.52	.45	.06	.13	.44	.47	.42	-	.02	.44	.40	.42	.04	.02	.44 - .44 (.58 in Rake)	
RAKE	H	.58	.30	.35	.28	.23	.44	.50	.50	-	-	.44	.40	.40	.04	.04	.44 - .44 (.58 in Rake)	
below	G	.58	.35	.35	.23	.23	.44	.07	.35	.37	.09	.44	.30	.32	.14	.12	.58 - .44	
"	F	.58	.37	.37	.21	.21	.44	.30	.35	.14	.09	.44	.37	.30	.07	.14		
"	E	.58	.50	.55	.08	.03	.46	.35	.32	.11	.14	.46	.37	.30	.09	.16		
"	D	.58	.50	.57	.08	.03	.46	.42	.35	.04	.11	.46	.45	.52	.01	-	.58 - .46	
"	C	.58	.55	.57	.03	.01	.46	.46	.22	-	.24	.46	.42	.30	.04	.16		
"	B	.58	.55	.55	.03	.03	.46	.44	.35	.02	.11	.46	.50	.55	-	-		
"	A	.58	.50	.45	.08	.13	.46	.48	.55	.10	.13	.46	.40	.37	.06	.09		
Keel		.68	.70	.70	-	-	.64					.64	-	-			.68 - .64	

Drillings at ends to be made in the vicinity of the peak bulkheads.

© 2020 Lloyd's Register Foundation

Transoms, Pointers & Crutches -
Timbers of Frame at openings -

efficient? No